



Chemical Resistance: Polyurethane Safety Mats

CHEMICAL COMPATIBILITY

Benzene	3
Toluene	4
Kerosene	1
Mineral Oil	1
White Oil	1
Fuel Oil	2
Naphta	2
Lubrificating Oils	2
Natural Gas	2
Hesane	2
Petroleum 250°F	2
Ethyl Benzine	4
Naphtaline	2
Turpentina	4
Nitric Acid Diluite	3
Sulfuric Acid Diluite	3
Phosphoric Acid Diluite	1
Hydrochloric Acid Concentrate	4
Formic Acid	3
Acetic Acid 30%	4
Citric Acid	1
Methanol	4
Benzil Alcohol	4
Etilic Alcohol	4
Cyclohexane	1
Glycerine	1
Potassium Hydroxide	4
Sodium Hydroxide	4
Ammonia 10%	2
Aniline	4
Barium Salt	2
Aluminium Chloride	3
Copper Chloride	1

Ratings:

- 1 = Little or no impact
- 2 = Minor effect
- 3 = Moderate effect
- 4 = Severe effect

The information contained in this technical sheet is based on our best technical and practical knowledge but does not constitute a specification and is given in good faith and without warranty.